

- **Presentation of Mortar:** Dry powder
- **Particle size:**  $\leq 0.3$  mm
- **Apparent specific gravity of the powder:** 1.40 Kg/dm<sup>3</sup>
- **Application:** Indoor / Outdoor
- **Slope of Application:** Vertical
- **Use Temperature:** 5 ° C to 30 ° C
- **Flammability:** Not flammable
- **Quantity of Water mixing:** 6 to 6.5 L of water / powder of 25Kg
- **pH:** 13
- **Color hardened mortar:** Grey
- **Volume weight of the fresh mortar:** 1.75 Kg / dm<sup>3</sup>
- **Resting time after mixing:** 5 minutes
- **Time of use of mortar:** 3 hours
- **Open time:** 20 minutes
- **Adjustability time:** 30 minutes
- **Timeout for placing the ceramic coating Candiwall:** 7 days
- **Waiting time between the end of the ceramic paste and the beginning of grouting:** 48 to 72 hours
- **Yield:** 6 kg/m<sup>2</sup>
- **Maximum thickness of application:** 10 mm
- **Water absorption by capillary:** EN 1015-18 - W2
- **Permeability to water vapor:** EN 1015-19,  $\mu \leq 15$
- **Adherence to the XPS concrete slab:** EN 1348  $\geq 0,25$  MPa CF-S
- **Adhesion of the brick slip to the concrete slab:** EN 1348  $\geq 1,0$  MPa CF-T
- **Adherence of the brick slip to the XPS:** EN 1348  $\geq 0,2$  MPa CF-S

Ver. 1.0/2012